Quality Matters

W)

ADMIX WP761

Capillary Crystallization Waterproofing System for Concrete

ADMIX WP761 is a perfect and permanent waterproofing material for concrete surfaces in order to control water leakage and moisture ingress. After application of this product in exposure of moisture, insoluble crystals form and expand in capillaries and micro cracks to provide permanent waterproofing for whole life of structure.

Applications

ADMIX WP761 can be applied in following methods:

- Preparation of slurry and applying in layers by means of paint brush or sprayer within two hours intervals, in which the first layer has set. For slurry preparation, mix 2 to 2.5 parts of powder to 1 part of clean water. Please note that water should be added to powder, so pour powder into the mixer first and then add water.
- Preparation of paste and applying on rough surfaces or in corners. Mixing method is the same as slurry, but mixing ratio of powder is more.
- As dry shake on fresh concrete or joints

Important notes

As the system is based on crystal formation and growth, surfaces have to be saturated before application, and applied materials should permanently be kept wet for 7 days by means of water curing.

Curing should start after initial setting and when surface discoloration starts.

Surface preparation

Before application of **ADMIX WP761**, surface capillaries should be opened by means of sand blasting or wire brushing. Any contamination, oil and grease, curing compound and paint should be removed and cleaned. Larger cracks and damaged areas should be repaired and leveled by cement-based repair mortars, then applying waterproofing material.

Consumption



White Damavand Corporation

4th Floor, No.13, West 35th St. Alvand Ave., Argentina Sqr., Tehran, Iran

Tel: +98 (21) 8867 8880

http://white-damavand.ir

ら

Quality Matters

For waterproofing one square meter with slurry method in the thickness of 1mm, two kg of powder is required. For applying paste in 3 to 4 mm thickness, 6 to 8 kg of powder is needed. The consumption can be greater on uneven surfaces.

Packaging

ADMIX WP761 is supplied in 25 kg PP bags.

Storage

ADMIX WP761 must be stored in original packages on pallets and be protected from sunlight, compaction and moisture. Shelf life of the products is 12 months.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product. For specific storage condition contact **White Damavand** Technical Services Department.

Safety awareness

Like other cement-based products, **ADMIX WP761** may cause minor irritation. Use personal safety devices while using this material. In case of any contact to eyes or skin, wash it with clean water for at least 15 minutes and get medical helps.

Quality approval

All materials produced in **White Damavand** are under strict control of QC department and meet the requirements of international standards.

Supplementary data

For any additional information, please contact company's specialists.



White Damavand Corporation

4th Floor, No.13, West 35th St. Alvand Ave., Argentina Sqr., Tehran, Iran

Tel: +98 (21) 8867 8880